
THERMAL PROTECTIVE PERFORMANCE REPORT

File name 080214GC
Test time Thu 14-Feb-08 15:57
Fabric type Kombat 750 Blk.
Fabric weight 7.5 oz/yd²
Fabric thickness 0 mils
Heat flux 1.96 cal/(cm²*sec)
Avg scan interval .22 sec
Head distance 0 in
TPP time 21.9 sec
TPP value 42.8 cal/cm²
FFF value 5.7 (cal/cm²)/(oz/yd²)
Pain time 15.1 sec

Comments:
Tab# 30485
Kombat 750 Blk.
x-tech
Aralite SL3

THERMAL PROTECTIVE PERFORMANCE

